Reliability Report

Issue Date 2015/3/13 Doc. No. IRC-BS-2E-A

1. Reliability Test Results

Group	Test Items	Test Conditions	Test Quantity	Failure Quantity	Remarks
1	Solderability	Solder Temperature 230°C Immersion Time 5sec Using rosin-type flux	45	0	
2	Resistance to solder heat	Solder Temperature 260°C Immersion Time 10sec Immersing 1.5mm to the root of leads	22	0	
3	Whisker	60°C, 90%RH, 4000hr −40°C, 85°C, 30 min each, 1500 cycles Room Temperature 8760hr	20	0	
4	Temperature Cycle	Ta=Tstg(min) ~ Tstg(max) 30min each cycle 100 cycles	45	0	
5	Humidity Resistance	Ta=85°C, 85%RH 1000hr	45	0	
6	High Temperature Storage	Ta=Tstg(max) 1000hr	45	0	
7	Operation life test	Ta=25°C IT=IT(max) 1000hr	45	0	
8	Electrostatic Breakdown Resistance	C=200pF, 0Ω Applied Voltage ±200V Applied once on each pin	11	0	
9	Teriminal Strength	2.45N, 90°, Bending twice	22	0	

2. Failure Criteria

Jillena					
Group		Failure Criteria			
1	Less than 95% of the immersed	Less than 95% of the immersed part is covered with solder.			
3	50µ m or more	50μ m or more			
9	An abnormality is observed suc	An abnormality is observed such as broken lead.			
2, 4~9	Measurement items	Failure Criteria			
	VS	Which does not meet the electrical characteristics.			
	IS	which does not meet the electrical characteristics.			
	ID	Which does not meet the electrical characteristics. Whose change rate exceeds $\pm 20\%$.			
	Visual Check	An apparent change in appearance is observed.			

Measurement conditions are based on the corresponding specification sheet.

For further information of the contents above, please contact our Business Department.